



HANDY ONE[®] AL 802

This proprietary family of brazing & soldering products eliminates the need for a separate fluxing operation, which can result in a significant increase in productivity while minimizing flux exposure to your personnel and plant equipment.

NOMINAL COMPOSITION

Aluminum	2.0% ± 0.5%
Zinc	Remainder
Other Elements (Each)	0.05% Max
Other Elements (Total)	0.15% Max

PHYSICAL PROPERTIES

Color	Grayish-White
Melting Point (Solidus)	710°F (377°C)
Flow Point (Liquidus)	725°F (385°C)
Brazing Range	725°F - 755°F (385°C - 402°C)
Specific Gravity	6.91
Density (Lbs/in ³)	0.25
Electrical Conductivity (% IACS) ⁽¹⁾	N/A
Electrical Resistivity (Microhm-cm)	N/A

⁽¹⁾ IACS = International Annealed Copper Standard

PRODUCT USES

AL 802 is a general purpose, free flowing soft soldering filler metal for joining of all solderable grades of aluminum and aluminum alloys when using open air heating methods.

PROPERTIES OF SOLDER JOINTS

The properties of a solder joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal. Joint clearances of 0.003 - 0.005 in (0.076-0.127 mm) per side are optimum for achieving highest joint strength. Joints with increased clearances can still produce adequate joint strengths depending on final operating conditions. Zinc based alloys offer the highest strength in comparison to other commercially available low temperature aluminum soldering alloys often surpassing shear strengths of 18,000 PSI as long as proper joint design techniques are implemented.

AVAILABLE FORMS

Flux cored wire and preforms. Two grades of flux are available for the flux cored product:

1. 50:50 ratio Cs based flux: lower melting flux for shorter heating cycles
2. 60:40 ration Cs based flux: slightly higher melting flux with longer life for extended heating cycles

SPECIFICATIONS

AL 802 alloy conforms to the following specifications: N/A



Technical Data Sheet

APPLICABLE PRODUCT CODE(S)

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: 30-802.

Distribution P/N: 99087, 99088.

SAFETY INFORMATION

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for Handy One AI 802.

WARRANTY CLAUSE

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.